

Technical  
Data Sheet



Distributed by:  
PRP CO.  
281.778.3223

Partnering through service,  
innovation, and integrity

# FastPatch 5000

## High Strength Concrete Repair

### DESCRIPTION

FastPatch 5000 is a flexible and tough concrete repair material with excellent adhesion. FastPatch 5000 is a 100% solids, 2-component urethane designed to meet 5,000 psi compression strength requirements combined with excellent flexibility and resilience. Areas repaired with FastPatch 5000 can be re-opened to traffic in less than one hour.

### WHERE TO USE

- Roads/Highways
- Bridges
- Warehouse Floors
- Parking Decks
- Sidewalks
- Any Crack or Spall in Concrete Needing Repair

### FEATURES AND BENEFITS

- **Rapid cure**— as little as 1 hour return to service
- **100% Solids, no odor**
- **1:1 Ratio by volume**—easy application
- **Excellent concrete adhesion**
- **Minimal equipment requirements**
- **Ideal for concrete repairs where high strength material is required**

### PACKAGING

- 20-oz. (600 mL) Cartridge
- 50-oz. (1500 mL) Cartridge

FastPatch 5000 Kit (aggregate included)  
FastPatch 5000 High-Yield Kit

- 5-Gallon (19-Liter) Pail
- 50-Gallon (190-Liter) Drum
- 200-Gallon (757-Liter) Tote

### COLORS

Gray

### SHELF LIFE

1 year when properly stored.

### STORAGE

Store and ship this product in clean, dry, low-humidity, and shaded or covered environments between 50 and 90°F (10-32°C)

## TYPICAL PROPERTIES

	Result	ASTM
Solids Content	100%, SCAQMD compliant	D2369
Tack-Free Time	10 minutes	C679
Concrete Adhesion, Unprimed	600 psi (4.1 MPa), concrete failure	D4541
Concrete Adhesion, Primed	1,200 psi (8.3 MPa), concrete failure	D4541
Compression Strength, gravel aggregate, 3.5 hour ambient cure	1,500 psi (10.3 MPa)	C109
Compression Strength, gravel aggregate, 158°F (70°C) overnight cure	5,000 psi (34.5 MPa)	C109
Hardness	70 Shore D	C661
Mix Ratio (by Volume)	1:1	-

## APPLICATION INSTRUCTIONS

For instructions on how to handle and apply FastPatch 5000 from cartridges, please refer to [POLYQuik® Cartridge Instructions](#). For handling and applying from kits: [POLYQuik® Kit Instructions](#). For applications with WVCO/Pre-Tec metering equipment, training will be provided. If you have specific questions related to your dispensing equipment, please contact your WVCO representative or customer support.

For concrete spall and crack repair guidelines, please refer to: [POLYQuik® Concrete Spall and Crack Repair Guidelines](#)

For bridge header repair guidelines, please refer to: [POLYQuik® Bridge Header and Joint Installation Guidelines](#)

## ESTIMATED COVERAGE

Crack filling (without aggregate)

Crack Dimensions	Linear Feet (Meter) per 20 oz. (600 mL) Cartridge	Linear Feet (Meter) per Gallon (3.8 Liter)
1/8' x 1/2' (3.2 x 12.7 mm)	14.8 (4.5)	95 (29)
1/4' x 1/2' (6.4 x 12.7 mm)	7.4 (2.3)	47 (14)
1/2' x 1/2' (12.7 x 12.7 mm)	3.7 (1.1)	24 (7.2)
1' x 1/2' (25.4 x 12.7 mm)	1.8 (0.6)	12 (3.6)

Concrete repair yield-volumes are with aggregate. Coverage area assumes 2" (51 mm) average repair depth.

	Yield	Coverage Area ft <sup>2</sup> (m <sup>2</sup> )
20 oz (600 mL) cart.	90 in3 (1.5 liters)	0.31 (0.03)
50 oz (1500 mL) cart.	225 in3 (3.7 liters)	0.78 (0.07)
1 gallon (3.8 liter) of mixed material	2.5 gallons (9.5 liters)	2.01 (0.19)
FastPatch 5000 Kit	2.5 gallons (9.5 liters)	2.01 (0.19)
FastPatch 5000 High Yield Kit	5 gallons (19 liters)	4.01 (0.373)

## HEALTH AND SAFETY

Before handling, you should become familiar with the Safety Data Sheet (SDS) regarding the risks and safe use of this product. To obtain an SDS, please call 800-333-9826 or send an email to: [msds@wilvaco.com](mailto:msds@wilvaco.com).

### DISCLAIMER OF WARRANTY

TEST RESULTS ARE TO BE CONSIDERED AS REPRESENTATIVE OF CURRENT PRODUCTION AND SHOULD NOT BE TREATED AS SPECIFICATIONS. WHILE ALL THE INFORMATION PRESENTED IN THIS DOCUMENT IS BELIEVED TO BE RELIABLE AND TO REPRESENT THE BEST AVAILABLE DATA ON THESE PRODUCTS, NO GUARANTEE, WARRANTY, OR REPRESENTATION IS MADE, INTENDED, OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION, OR AS TO THE SUITABILITY OF ANY CHEMICAL COMPOUNDS FOR ANY PARTICULAR USE, OR THAT ANY CHEMICAL COMPOUNDS OR USE THEREOF ARE NOT SUBJECT TO A CLAIM BY A THIRD PARTY FOR INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT. EACH USER SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE. PROPER APPLICATION IS THE RESPONSIBILITY OF THE USER. AS WITH ANY PRODUCT THE USE OF THIS PRODUCT IN A GIVEN APPLICATION MUST BE TESTED (INCLUDING BUT NOT LIMITED TO FIELD TESTING) IN ADVANCE BY THE USER TO DETERMINE SUITABILITY. TESTING IS THE REQUIREMENT OF BOTH ENGINEERS AND CONTRACTORS ALIKE. WVCO DOES NOT WARRANT THE APPLICATION UNDER ANY OR ALL CIRCUMSTANCES.

Distributed by:  
PRP CO.

281.778.3223

### DIVISIONS

#### WESTERN DIVISION

1075 Arrowsmith Street  
PO Box 2280  
Eugene, OR 97402  
Tel 541.484.9621  
[www.POLYQUIK.com](http://www.POLYQUIK.com)  
[www.SPIKEFAST.com](http://www.SPIKEFAST.com)

#### EASTERN DIVISION

6662 Marbut Road  
Lithonia, GA 30058  
Tel 888.878.9826

#### MIDWEST DIVISION

1549 Hwy 2  
Two Harbors, MN 55616  
Tel 218.834.3922

#### PRECISION TECHNOLOGIES DIVISION

675 McKinley Street  
Eugene, OR 97402  
Tel 541.484.2368  
[www.pre-tec.com](http://www.pre-tec.com)

#### SOUTHERN DIVISION

100 Dixie Mae Drive  
PO Box 4450  
Pineville, Louisiana 71361  
Tel 318.640.5077

### SUBSIDIARIES

#### CANADIAN WILLAMETTE

19081- 27th Avenue  
Surrey BC V3S 5T1  
Tel. 800.663.4298

#### ECLECTIC PRODUCTS INC.

Corporate Office  
1075 Arrowsmith Street  
Eugene, OR 97402  
Tel 541.284.4667  
[www.eclecticproducts.com](http://www.eclecticproducts.com)

#### IDAHO MILL & GRAIN

445 North 430 West Hwy  
PO Box 188  
Malad City, Idaho 83252  
Tel 208.766.2206

#### TAPEL WILLAMETTE LTD. S.A.

Av. Estero La Posada 3625  
Parque Industrial Coronel  
Coronel, Chile  
Tel 011.56.41.2.928.100  
[www.tapel.cl](http://www.tapel.cl)



Revision Date: November 2014